Application News

Total Organic Carbon Analysis

Carbon Measurement of Oil Shale

No. **071**



Oil shale, also called kerogen shale, is a type of sedimentary rock that has a high content of hydrocarbons in the stage prior to petroleum. The gas obtained by heating oil shale is called oil shale gas, while the natural gas enclosed in fine cracks in sedimentary rocks is called shale gas. In some cases, oil shale is used for power generation and heating by direct combustion. As high expectations are placed on oil shale as an energy source, the carbon content of oil shale is an important factor.

The system using Shimadzu TOC-L total organic carbon analyzer and SSM-5000A solid sample combustion unit measures the carbon content of solid samples by direct combustion at high temperature. This system does not require extraction or other troublesome pretreatment, and enables measurement of the total carbon content with a high recovery rate and accuracy. This article introduces an example of measurement of the total carbon content of oil shale by using the abovementioned system.

Y. Ikezawa

Sample Preparation

Because natural gas has accumulated in the crevices in the sedimentary rock called oil shale, there is a possibility of explosion due to rapid heating if oil shale is measured in lump form. Therefore, part of the sample material (Fig. 1) was broken up and crushed using an agate mortar (Fig. 2), and the powdery oil shale was placed in sample boat for use as the measurement sample.



Fig. 1 Oil Shale







Fig. 3 Measurement Sample



Direct Combustion Method Using TOC Solid Sample Measurement System

- Does not require extraction or other pretreatment, and has high recovery rate and accuracy.
- Does not require chemicals.
- Quick measurement time of approximately 5 min.
- Sample boat is reusable.

■ TOC Solid Sample Measurement System


The TOC solid sample measurement system, comprising the TOC-L total organic carbon analyzer and SSM-5000A solid sample combustion unit, quantifies the organic content of solid samples by combustion oxidation of the organic matter in the sample and detection of the formed carbon dioxide (CO₂). Because the organic matter contained in a sample can be measured by direct combustion of the sample, quick and simple organic analysis without extraction or other troublesome pretreatment processes is possible. Table 1 shows the measurement conditions.


Table 1 Measurement Conditions

Tuble 1 Measurement Conditions		
Analyzer	: TOC solid sample measurement system TOC-L _{CPH} total organic carbon analyzer + SSM-5000A solid sample combustion uni (Cell switching valve set: Specification A)	
Cell length	: Short cell	
SSM carrier gas	: Oxygen gas, 400 mL/min	
TC oxidation method	: Combustion catalytic oxidation	
	(Combustion temperature: 900 °C)	
Measurement item	: TC (Total carbon)	
Calibration curve	: One-point calibration curve using 1 % C glucose solution	

Preparation of Calibration Curve

The calibration curve was prepared by adding 500 μL of a 1 % C (carbon concentration: 1 %) glucose solution to ceramic fiber in the sample boat, and performing the TC measurement (Fig. 4).





1 % C glucose solution Fig. 4 Measurement Data of Calibration Curve

Results of Sample Measurement

Approximately 130 mg of the powdered oil shale was weighed out into the sample boat for each measurement, and three measurements performed. Table 2 shows the measurement results, and Fig. 5 shows the peak data obtained by the measurements. From the measurement results, the oil shale prepared for this study contained approximately 3.6 % carbon. The CV value of the concentration obtained from the three measurements was 1.37 %, showing that the measurements were conducted with good repeatability. The carbon content in rock such as oil shale can be quantified if the TOC solid sample measurement system is used.

Table 2 Measurement Results

Measurement No.	Total carbon content (%)
1	3.62
2	3.60
3	3.52
Average	3.58




Fig. 5 Measurement Data



Shimadzu Corporation

www.shimadzu.com/an/

For Research Use Only. Not for use in diagnostic procedures.

This publication may contain references to products that are not available in your country. Please contact us to check the availability of these products in your country

The content of this publication shall not be reproduced, altered or sold for any commercial purpose without the written approval of Shimadzu. Shimadzu disclaims any proprietary interest in trademarks and trade names used in this publication other than its own. See http://www.shimadzu.com/about/trademarks/index.html for details.

The information contained herein is provided to you "as is" without warranty of any kind including without limitation warranties as to its accuracy or completeness. Shimadzu does not assume any responsibility or liability for any damage, whether direct or indirect, relating to the use of this publication. This publication is based upon the information available to Shimadzu on or before the date of publication, and subject

First Edition: Jul 2018

Related Products Some products may be updated to newer models.



Related Solutions

