

# Application Data Sheet

### **Autograph Precision Universal Tester**

## No. C

### Tear Tests of Angle-Shaped Rubber Specimens

Standard No. ISO34-1: 2004 (JIS K6252: 2007)

#### Introduction

Rubber materials have characteristic mechanical properties including elasticity and flexibility, and are widely used for industrial parts, construction materials, and housewares. In particular, a diverse range of synthetic rubber materials with differing properties suited to match their application have been developed. Measuring these mechanical properties is extremely important to ensure quality control and for new materials development. This Data Sheet introduces an example of the evaluation of two synthetic rubber specimens (angle-shaped specimens). Tear tests were performed, and the specimens were evaluated with respect to tear strength, one of their basic mechanical properties.

T. Murakami, J. Sakai

#### Measurements and Jigs

Tear tests of angle-shaped rubber specimens require grips that tighten automatically as the tear force increases. When tensile loads are applied to rubber materials, they elongate and their thickness decreases. For this reason, if there is no automatic tightening mechanism, the specimen will inadvertently break free of the grips before the maximum tear force is applied, making favorable measurements impossible. Accordingly, in rubber tear tests, it is necessary to use pneumatic parallel grippers, pantograph grips, eccentric roller type grips, Henry Scott type grips, or other grips equipped with this feature.

#### Measurement Results



Fig. 1: Test Status

25										
22 -										
20 –				Α		<b>\</b>				
18 –				<b>~</b>		N/				
16 –						///				
≘ <sup>14</sup> -							THE			
<del>ε</del> 12 -		,		A STATE OF THE STA		- 11	- \	В		
Force (N)			A STATE OF THE STA							
<sup>L</sup> 8 -										
6 -										
4 - /										
2 -//	7									
0 🔼							1			
0	6	12	18	24	30	36	42	48	54	60
			Dis	splace	ment	(mm)				

Fig. 2: Relationship Between Force and Displacement

#### Table 1: Test Conditions

Item	Set Value
Test Speed	500 mm/min
Initial Distance between Grips	60 mm

Table 2: Test Results (Average)

	(N)	(kN/m)
rubber (black)	19.7	9.85
rubber (white)	14.7	7.35
	,	` ,

The tear test results for the two samples are shown in Table 2. A graph showing the force-displacement relationship for each sample is shown in Fig. 2. Differences in tear strength between the samples are clearly apparent.

#### Rubber Tear Test System

Tester: AGS-X Load Cell: 1 kN

Test Jig: 1 kN pneumatic flat grips (Single-side file teeth grip faces)

Software: TRAPEZIUM LITE X







AGS-X Table-Top Precision Universal Tester

#### **Features**

- A high-precision load cell is adopted. (The high-precision type is class 0.5; the standard-precision type is class 1.) Accuracy is guaranteed over a wide range, from 1/500 to 1/1 of the load cell capacity. This supports highly reliable test evaluations.
- Crosshead speed range Tests can be performed over a wide range from 0.001 mm/min to 1,000 mm/min.
- High-speed sampling High-speed sampling, as fast as 1 msec.
- TRAPEZIUMX LITE X operational software This is simple, highly effective software.
- Jog controller (optional)

  This allows hand-held control of the crosshead position. Fine position adjustment is possible using the jog dial.
- Optional Test Devices
   A variety of tests can be conducted by switching between an abundance of jigs in the lineup.

to change without notice

The information contained herein is provided to you "as is" without warranty of any kind including without limitation warranties as to its accuracy or completeness. Shimadzu does not assume any responsibility or liability for any damage, whether direct or indirect, relating to the use of this publication. This publication is based upon the information available to Shimadzu on or before the date of publication, and subject

### **Related Products** Some products may be updated to newer models.





- Price Inquiry
- > Product Inquiry
- > Technical Service / Support Inquiry
- Other Inquiry